

H 75012

Blockbitumen B 85/25

Product	Solvent-free bitumen mass
Standard	EN 13304
Intended use	Hot-setting bitumen mass for the bonding of bituminous membranes
Application	Pour- and roll method (hot-setting adhesive)
Packaging	Blocks in cardboard-boxes of app. 22 kg, 21 blocks per pallet

Characteristics	Testing method	Unit	Result
Color			black
Density	EN ISO 3838	g/cm ³	1,0 – 1,1
Needle penetration at 25°C	EN 1426	°C	20 -30
Softening point ring & ball method	EN 1427	°C	80 - 90
Breaking point	EN 12593	°C	≤ -10
Flashing point (Cleveland)	EN ISO 2592	°C	≥ 250

The declared data are indices based on the statistical quality control and refer to the date of production. Consider state of the art, standards, legal provisions and guidelines for the suitability of the mentioned field of application and application method. All specifications are without obligation. The user must assess the suitability of the product for the particular purpose and ensure the user's access to the current version of the product data sheet.

Subject to alteration without notice.

Storage conditions: The products have to be stored in original packaging, being protected from direct sun light, UV-beams and extreme conditions like heat, frost, moisture, etc. During cold season store the products in a frost-free area (+5°C) for 12 hours before application.

Development, Production and Sales of our products according to ISO 9001.